## **TECHNICAL SPECIFICATION**



JI 3 TAPE

# **JLN-1840 Natural**

### **SELF-ADHESIVE KRAFT PAPER TAPE**

Physical Properties	Standard	Metric	Test Method	
Color	Natural			
Adhesive	Hot Melt Adhesive			
Backing	80 g/m Kraft Paper			
Total Thickness	6.7 mils	0.17 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	83 oz/in	23 N/25mm	ASTM D-3330	GB/T2792
Holding Power	>48 h	>48 h	ASTM D-3654	GB/T4851
Tensile Strength	27 lbs/in	120 N/25mm	ASTM D-3759	GB/T7753
Elongation at Break	1.5-3%	1.5-3%	ASTM D-3759	GB/T7753
Service TemMini	<b>23</b> °F	<b>-5</b> ℃	BC/BD-220SE	BC/BD-220SE
Service TemMax	140°F	60°C	DHG-9055A	DHG-9055A

#### **DESCRIPTION**

JLN-1840 flatback packaging tape is a quick, sure sealing, economical, pressure-sensitive flatback tape which can increase packaging line efficiency. It is versatile and offers a positive attractive seal which matches most corrugated cardboard. It's quick stick and has excellent adhesion which discourages pilfering. It can be used on all types of cartons.

#### **PRODUCT APPLICATION**

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads.

#### **STORAGE CONDITION**

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

#### FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

No.11 Xiazhai Road, Jiulong Industry Park, Hua An, Zhangzhou, Fujian 363000 China. Tel:+86-592-207-5506 info@jl3tape.com http://www.jl3tape.com









