



FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

NO.11 XIAZHAI ROAD, JIULONG INDUSTRY PARK, HUA AN ECONOMIC DEVELOPMENT ZONE, HUA AN COUNTY, ZHANGZHOU CITY, FUJIAN 363000 CHINA Tel:+86-596-728-0001 Fax:+86-596-728-8003 http://www.jl3tape.com/

JLT-695

PRODUCT DESCRIPTION

JLT-695 Backed with PET film and reinforced with glass fiber. It's high strength mono-directional filament tape with good resistance to abrasion, oil and high temperature. Suitable for transformers, coils and motor parts strapping and fixing.

PERFORMANCE FEATURES

JLT-695 is a transparent and high strength filament tape. Glass fiber contributes higher tensile strength and improved pressure-sensitive adhesive delivers high viscosity and tensile strength; high resistance to abrasion; impact resistance and high holding power.

STORAGE CONDITION

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4 to 26 °C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

BRANCHES:

SHANGHAI JIALONG FIBER TAPE CO.,LTD.

No.211, Yuxin Rd, Songjiang Dist, Shanghai, China.

JIALONG GROUP PTY LTD.

Unit 83, 79 St Hilliers Road Auburn NSW 2144,

Australia.

Mono-Directional Filament Tape

| Physical Properties | Standard | Metric | Test Method | |
|---------------------|-------------------------------------|-----------|-------------|-------------|
| Reinforcement | Fiberglass | | | |
| Adhesive | Acrylic Pressure-Sensitive Adhesive | | | |
| Backing | PET | | | |
| Color | Clear | | | |
| Total Thickness | 5.9 mils | 0.15 mm | ASTM D-3652 | GB/T7125 |
| Peel Adhesion | 58 oz/in | 16N/25mm | ASTM D-3330 | GB/T2792 |
| Holding Power | ≥24 h | ≥24 h | ASTM D-3654 | GB/T4851 |
| Tensile Strength | 214 lbs/in | 950N/25mm | ASTM D-3759 | GB/T7753 |
| Elongation at Break | 3% | 3% | ASTM D-3759 | GB/T7753 |
| Service Tem.--Mini | 23°F | -5°C | BC/BD-220SE | BC/BD-220SE |
| Service Tem.--Max | 158°F | 70°C | DHG-9055A | DHG-9055A |

Other dimensions available upon request.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

