



JLT-607D

Mono-Directional Filament Tape

| Physical Properties | Standard | Metric | Test Method | |
|---------------------|------------------|-----------|-------------|-------------|
| Reinforcement | Fiberglass | | | |
| Adhesive | Synthetic Rubber | | | |
| Backing | PET | | | |
| Color | Milk White | | | |
| Total Thickness | 5.5 mils | 0.14 mm | ASTM D-3652 | GB/T7125 |
| Peel Adhesion 90° | 94 oz/in | 26N/25mm | ASTM D-3330 | GB/T2792 |
| Holding Power | ≥48 h | ≥48 h | ASTM D-3654 | GB/T4851 |
| Tensile strength | 214 lbs/in | 950N/25mm | ASTM D-3759 | GB/T7753 |
| Elongation at Break | 3% | 3% | ASTM D-3759 | GB/T7753 |
| Service Tem.--Mini | 23°F | -5°C | BC/BD-220SE | BC/BD-220SE |
| Service Tem.--Max | 158°F | 70°C | DHG-9055A | DHG-9055A |

DESCRIPTION

JLT-607D Backed with PET film and reinforced with glass fiber. It's milk white and dense mono-directional filament tape with high strength; special adhesive with sweet smell; suitable for steel cable bundling and special package fixing.

PERFORMANCE FEATURES

JLT-607D is a milk white and sweet smell filament tape with high strength. Glass fiber contributes higher tensile strength and improved special synthetic rubber delivers stronger adhesion; high resistance to abrasion; impact resistance and high holding power.

STORAGE CONDITION

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

No.11 Xiazhai Road, Jiulong Industry Park, Hua An, Zhangzhou, Fujian 363000 China.
Tel:+86-592-207-5506

info@jl3tape.com <http://www.jl3tape.com>

